
FACADEO 1060



THICKNESS mm	WEIGHT kg/m²
0.63	5.53
0.75	6.58

STANDARD COATINGS ›

Steel S 350 GD	Thickness mm	Standards
Galva	0.63/0.75	NF EN 10346 / NF P 34-310
Polyester 25µ/35µ	0.63/0.75	NF EN 10169 / NF P 34-301
Other coatings	on request	NF EN 10169 / NF P 34-301

BUREAU VERITAS

TEST REPORT › NO. LAB 79450601

Deflection tests according to NF P 34-503 of November 1995. Professional rules for the manufacture and installation of metal cladding (January 1981 - 2nd edition)

LOAD TABLE IN daN/m² ACCORDING TO USE SPANS › fy: 350MPa - nominal thicknesses in mm

PRESSURE				USE SPANS m	DEPRESSION			
0.63	0.75	0.63	0.75		0.63	0.75	0.63	0.75
248		230		**1.50**			189	225
209		203		**1.60**	254		168	200
179	213	181	215	**1.70**	212		150	179
154	183	162	193	**1.80**	180	214	133	158
134	160	146	174	**1.90**	153	182	119	142
118	140	132	157	**2.00**	132	157	108	129
99	118	121	144	**2.10**	114	136	97	115
84	100	110	131	**2.20**	99	118	89	106
71	85	102	121	**2.30**	87	104	81	96
61	73	92	110	**2.40**	77	92	77	92
52	62	84	100	**2.50**	68	81	73	87
45	54	77	92	**2.60**	60	71	69	82
39	46	69	82	**2.70**	54	64	66	79
	40	61	73	**2.80**	48	57	63	75
	35	55	65	**2.90**	44	52	59	70
		50	60	**3.00**	39	46	57	68
			54	**3.10**			54	64
			49	**3.20**			51	61
				3.30			49	58
				3.40			47	56
				3.50			45	54

Seismic validation: CTSB study report DCC / CLC_12_229_1 dated 25/02/2013