



FACADEO 8.25



Pre-painted Surface

Option curving



THICKNESS mm	WEIGHT kg/m ²
0.63	5.86
0.75	6.97

STANDARD COATINGS >

Steel S 320 GD	Thickness mm	Standards
Galva	0.63/0.75	NF EN 10346 / NF P 34-310
Polyester 25μ/35μ	0.63/0.75	NF EN 10169 / NF P 34-301
Other coatings	on request	NF EN 10169 / NF P 34-301

**BUREAU
VERITAS**

TEST REPORT > NO. 1702353/1G

Deflection tests according to NF P 34-503 of November 1995. Professional rules for the manufacture and installation of metal cladding (January 1981 - 2nd edition)

LOAD TABLE IN daN/m² ACCORDING TO USE SPANS > fy: 320MPa - nominal thicknesses in mm

PRESSURE				USE SPANS m	DEPRESSION			
0.63	0.75	0.63	0.75		0.63	0.75	0.63	0.75
209		390		1.40	172		176	
188	223	355	423	1.45	155	184	166	198
169	201	323	384	1.50	140	167	157	187
153	182	294	350	1.55	127	151	148	177
138	165	269	321	1.60	116	138	141	167
126	150	247	294	1.65	105	126	133	159
115	137	227	271	1.70	97	115	127	151
105	125	210	250	1.75	89	105	120	143
96	114	194	231	1.80	82	97	115	136
89	106	180	214	1.85	77	92	109	130
83	99	167	199	1.90	73	86	104	124
77	92	155	185	1.95	69	82	100	118
72	86	145	172	2.00	65	78	95	113
68	81	135	161	2.05	62	74	91	108
64	76	126	151	2.10	59	70	87	104
60	71	119	141	2.15	56	67	84	100
56	67	111	132	2.20	53	63	80	95
53	63	105	125	2.25	51	60	77	92
50	60	99	117	2.30	49	58	74	88
47	56	92	109	2.35	46	55	71	85
45	53	86	102	2.40	44	53	68	81
42	50	80	95	2.45	42	51	65	78
40	48	75	89	2.50	41	48	63	75
		70	83	2.55			61	72
		65	78	2.6			58	69
		61	73	2.65			56	67
		58	69	2.7			54	65
		54	65	2.75			52	62
		51	61	2.8			51	60
		48	57	2.85			49	58
		45	54	2.9			47	56
		43	51	2.95			46	54
		40	48	3.00			44	53